# Sumitomo Silicone SI 9002N-1

### Silicone

Sumitomo Bakelite North America, Inc.

#### Message:

SI 9002N-1 is a short fiberglass reinforced silicone molding compound, which offers moderate strength properties, and dimensional stability and excellent long-term thermal stability at elevated temperatures.

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Good Dimensional Stability		
	Good Strength		
	Good Thermal Stability		
Appearance	Red		
Forms	Granules		
Processing Method	Compression Molding		
	Resin Transfer Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.10	g/cm <sup>3</sup>	ASTM D792
Apparent Density	0.90	g/cm <sup>3</sup>	ASTM D1895
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Water Absorption - 48 hr (50°C)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale, Compression Molded)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression			
Molded)	27.0	MPa	ASTM D638
Flexural Modulus (Compression Molded)	14000	MPa	ASTM D790
Flexural Strength (Break)	52.0	MPa	ASTM D790
Compressive Strength	88.0	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	22	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed, Compression Molded)	> 282	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength <sup>1</sup>			ASTM D149
<sup>2</sup>	9.8	kV/mm	
<sup>3</sup>	6.5	kV/mm	

Dielectric Constant <sup>4</sup> (1 MHz)	3.90		ASTM D2520
Dissipation Factor <sup>5</sup> (1 MHz)	0.020		ASTM D150
Arc Resistance	200	sec	ASTM D495
NOTE			
1.	Wet, 60 Hz		
2.	Method A (Short-Time)		
3.	Method B (Step-by-Step)		
4.	Wet		
5.	Wet		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

