

SPESIN® KP213G30BK

Polybutylene Terephthalate

Kolon Plastics, Inc.

Message:

SPESIN® KP213G30BK is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E190675-100647285		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 1.0	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	137	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus (23°C)	8340	MPa	ASTM D790
Flexural Strength (23°C)	211	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	205	°C	
Peak Melting Temperature	224	°C	ASTM D3418
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	30	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.20		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

