

ALTECH® PC ECO 2020/140

Polycarbonate
ALBIS PLASTIC GmbH

Message:

ALTECH®PC ECO 2020/140 is a polycarbonate (PC) product that contains 20% glass fiber reinforced materials. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region.

Features include:

- flame retardant/rated flame
- Comply with REACH standard
- ROHS certification
- Flame Retardant
- Impact modification

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	Impact modifier		
	Flame retardancy		
Features	Impact modification		
	Good demoulding performance		
	Flame retardancy		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	8.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6800	MPa	ISO 527-2
Tensile Stress	70.0	MPa	ISO 527-2
Flexural Modulus	5400	MPa	ISO 178
Flexural Stress	160	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	30	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	135	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50
Flammability	Nominal Value	Test Method	
Flame Rating (1.5 mm)	HB	UL 94	
Injection	Nominal Value	Unit	

Drying Temperature - Desiccant Dryer	120	°C
Drying Time - Desiccant Dryer	2.0 - 6.0	hr
Processing (Melt) Temp	280 - 300	°C
Mold Temperature	80 - 120	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

