

# RJM SD101G10-W

Polycarbonate  
RJM International, Inc.

Message:

RJM SD101G10-W is a Polycarbonate (PC) product filled with 10% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Additive/Masterbatch.  
Characteristics include:  
Flame Rated  
Flame Retardant  
Lubricated

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Additive	PTFE Lubricant		
Features	Flame Retardant		
	Lubricated		
Uses	Compounding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	65.7	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	3430	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Taber Abrasion Resistance	7.00	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	140	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	250 to 310	°C	
Mold Temperature	120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

