

S&E; Wire & Cable GPE2001E-ROHS

Polyethylene
S&E; Specialty Polymers, LLC

Message:
GPE2001E-ROHS flame retardant polyethylene compound designed for wire and cable applications. GPE2001E-ROHS complies with RoHS requirements. GPE2001E-ROHS is suitable for 75°C continuous use and 100°C Max intermittent temperature application.

General Information			
Features	Flame Retardant		
Uses	Wire & Cable Applications		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41 to 1.47	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	2.5 to 5.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	190	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	> 7.58	MPa	ASTM D412
Tensile Elongation (Break)	> 230	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	75.0	°C	
Maximum Use Temperature - Intermittent	100	°C	
Melting Temperature	85.0 to 125	°C	DSC
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	> 28	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT