## Nucrel® 960

## Ethylene Methacrylic Acid

## **DuPont Packaging & Industrial Polymers**

## Message:

Nucrel<sup>®</sup> 960 is a copolymer of ethylene and methacrylic acid, made with nominally 15 wt% methacrylic acid. It is inherently flexible without the need for plasticizers. The resin can be pigmented, UV-stabilized for exterior applications and painted or plated for special decorative effects.

General Information			
Features	Good Flexibility		
	Paintable		
	Platable		
Agency Ratings	FDA 21 CFR 177.1330(a)		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.940	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16	5		
kg)	60	g/10 min	ASTM D1238, ISO 1133
Methyl Acrylate Content	15.0	wt%	
Methacrylic Acid Content	15.0	wt%	
Freezing Point			
	73	°C	ISO 3146
	73	°C	ASTM D3418
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	62.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	91.0	°C	ASTM D3418, ISO 3146
Extrusion	Nominal Value	Unit	
Melt Temperature	< 235	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd. Tel: +86 21 5895 8519

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

