

# OCTAL PET DPET

Polyethylene Terephthalate

OCTAL Holding & Co.

## Message:

Clear Polyethylene Terephthalate (PET) sheet.

Plastic packaging products.

General Information			
Features	Amorphous Food Contact Acceptable		
Uses	Packaging Sheet		
Agency Ratings	EU Food Contact, Unspecified Rating FDA Food Contact, Unspecified Rating		
Appearance	Clear/Transparent		
Forms	Sheet		
Processing Method	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm <sup>3</sup>	ASTM D1503
Thickness <sup>1</sup>	200.0 to 1200.0	µm	
Core ID	152	mm	
Denest/Anti-block Treatment			
Available	Internal Anti-block Structure		
Standard	Surface Silicone Coating		
Roll Outer Diameter	100.00	cm	
Thermoforming Molding Temperature	121 to 154	°C	
Width - of sheet	< 168.00	cm	
Films	Nominal Value	Unit	Test Method
Film Thickness - Recommended / Available	200 to 1200 µm		
Tensile Strength - MD (Break)	55.3 to 62.2	MPa	ASTM D882
Optical	Nominal Value	Unit	Test Method
Transmittance	> 90.0	%	ASTM D1003
NOTE			

1. Variation: ±1%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

