

TEREZ PA/PP 7510 GF 20

Polyamide 6 + PP
TER HELL PLASTIC GMBH

Message:
20% glassfiber reinforced Blend, medium viscosity with high stiffness and low moisture absorption.
For moulding parts with high mechanical demand at low water absorption.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	High Stiffness		
	Low Moisture Absorption		
	Medium Viscosity		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6600	MPa	ISO 527-2
Tensile Strain (Yield)	1.9	%	ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	120	kN/m	ISO 34-1
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	63	kJ/m²	ISO 179/1eU

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT