Unipren® Elastomers A3 NTLA010 55A UP302

Styrene Ethylene Butylene Styrene Block Copolymer

Petropol Industry and Trade of Polymers LTDA

Message:

Unipren® Elastomers A3 NTLA010 55A UP302 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding. Important attributes of Unipren® Elastomers A3 NTLA010 55A UP302 are: Chemical Resistant Good Processability Good UV Resistance Typical applications include: Consumer Goods Household Applications Tools

General Information				
Features	Good Chemical Resistance			
	Good Processability			
	Good UV Resistance			
	Ozone Resistant			
	Soft			
Uses	Household Goods			
	Power/Other Tools			
	Toys			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.960	g/cm³	ASTM D792	
Molding Shrinkage - Flow	2.0 to 3.0	%	ASTM D955	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	52 to 58		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress ¹			ASTM D412	
100% Strain	1.80	MPa		
300% Strain	2.70	MPa		
Tensile Strength ² (Break)	5.00	MPa	ASTM D412	
Tensile Elongation ³ (Break)	600	%	ASTM D412	
Tear Strength ⁴	30.0	kN/m	ASTM D624	
Compression Set (70°C, 22 hr)	53	%	ASTM D395B	
Injection	Nominal Value	Unit		
Drying Temperature	80.0	°C		
Drying Time	2.0	hr		

Processing (Melt) Temp	180 to 200	°C	
Mold Temperature	25.0 to 50.0	°C	
NOTE			
1.	Die C		
2.	Die C		
3.	Die C		
4.	Die B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

