

LNP™ STAT-LOY™ 63000CT compound

Polycarbonate + Polyester
SABIC Innovative Plastics Asia Pacific

Message:
A permanent antistatic PC-Alloy compound that features transparency and superior cleanliness for advanced semiconductor packaging applications

General Information			
Features	Antistatic		
	Low (to None) Ion Content		
Uses	Packaging		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	16	g/10 min	ASTM D1238
Water Absorption (Equilibrium, 23°C, 50% RH)	0.70	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1160	MPa	ASTM D638
--	1180	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	35.0	MPa	ASTM D638
Yield	34.0	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	200	%	Internal Method
Break	140	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	1160	MPa	ASTM D790
-- ⁵	1140	MPa	ISO 178
Flexural Strength ⁶ (Break, 50.0 mm Span)	50.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	69	kJ/m ²	ISO 179/2C
Notched Izod Impact (23°C)	580	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 6.40 mm	83.0	°C	ASTM D648
1.8 MPa, Unannealed, 6.40 mm	73.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁷	68.0	°C	ISO 75-2/Af

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+11 to 5.0E+12	ohms	ASTM D257
Volume Resistivity	1.0E+11 to 5.0E+12	ohms·cm	ASTM D257
Static Decay ⁸	2.0	sec	FTMS 101B
Optical	Nominal Value	Unit	Test Method
Transmittance (2540 μm)	81.0	%	ASTM D1003
Haze (2540 μm)	10	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 95.0	°C	
Drying Time	6.0 to 8.0	hr	
Rear Temperature	220 to 230	°C	
Middle Temperature	225 to 240	°C	
Front Temperature	230 to 250	°C	
Nozzle Temperature	230 to 250	°C	
Processing (Melt) Temp	230 to 250	°C	
Mold Temperature	40.0 to 50.0	°C	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 10 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4 mm		
8.	5000V to <50V		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT