

Hostacom X 4323 3 S63 305514

Polypropylene Copolymer

LyondellBasell Industries

Message:

Hostacom X 4323/3 S63 305514 is a 20% talc filled PP copolymer, with low odour, low flowability and low emissions. Product is available as a customized color matched, pellet form. This grade is delivered in 305514 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Low volatilization		
	Copolymer		
	Low liquidity		
	The smell is low to none		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.06	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus ¹ (23°C)	2200	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.2	kJ/m ²	ISO 179/1eA
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT