

Axiall PVC 8805

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

General purpose, clear extrusion compound with good low temperature properties.

General Information			
Features	General Purpose		
	Good Flexibility		
	Low Temperature Flexibility		
Uses	General Purpose		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant	7.58	MPa	ASTM D638
Tensile Strength	17.2	MPa	ASTM D638
Tensile Elongation (Yield)	380	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-35.0	°C	ASTM D746
Melting Temperature	182	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT