

Karina IVORY PVC COMPOUND 105800-35/ 1-B-ISE-LMP

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

HEAVY METAL FREE PVC COMPOUND CLASS 105C (ST10) RECOMMENDED FOR JACKET OF ELECTRICAL CABLES.

General Information			
Uses	Cable Jacketing		
	Wire & Cable Applications		
Appearance	Ivory		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.31 to 1.37	g/cm ³	IEC 60811-1-3
Cadmium Content	< 50	ppm	IEC 62321
Chromium Content	< 100	ppm	IEC 62321
Color	OK		ME 12
Color a	-1.69 to 1.31		ME 12
Color b	4.75 to 7.75		ME 12
Color L	88.2 to 91.2		ME 12
Mercury Content	< 100	ppm	IEC 62321
Bromine Content	< 100	ppm	IEC 62321
Lead Content	< 100	ppm	IEC 62321
Maximum Variation of Elongation	< 25	%	IEC 60811-1-2
Maximum Variation of Tensile Strength	< 25	%	IEC 60811-1-2
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	78 to 82		NBR 7456
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	> 13.7	MPa	IEC 60811-1-1
Tensile Strain (Yield)	> 200	%	IEC 60811-1-1
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ²	> 13.7	MPa	IEC 60811-1-2
Tensile Elongation ³ (Break)	> 200	%	IEC 60811-1-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ⁴	> 1.0E+14	ohms · cm	NBR 5403
NOTE			
1.	24 hr		
2.	Aged in Air for 168 hr at 136°C		
3.	Aged in Air for 168 hr at 136°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

