ETILINAS MD20BK

Medium Density Polyethylene

POLYETHYLENE MALAYSIA SDN BHD

Message:

ETILINAS MD20BK is designed specifically for the manufacture of pipe and pipe fittings for use in potable water, gas and other high performance pressure pipeline systems.

ETILINAS MD20BK is based on a special medium density copolymer with exceptionally high resistance to environmental stress cracking and meets the ISO classification PE80 for pipe materials.

General Information	
Additive	Carbon black (2%)
Features	High ESCR (Stress Cracking Resistance)
	Copolymer
Uses	Piping system
	Accessories
Appearance	Black
Forms	Particle
Processing Method	Pipeline extrusion molding
	Extrusion

Physical	Nominal Value	Unit	Test Method
Density	0.947	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	0.85	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (F0)	1000	hr	ASTM D1693B
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	19.0	MPa	ISO 527-2/2
Tensile Strain (Break)	600	%	ISO 527-2/2
Flexural Modulus	750	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Vicat Softening Temperature	116	°C	ISO 306/A
CLTE - Flow (20 to 60°C)	1.5E-4	cm/cm/°C	ASTM D696
Additional Information			

Additional Information

Density of Compound, ISO 1872/1, Annealed: 949 kg/m³Carbon Black Content, ISO 6964: 2.25%Minimum Required Strength (MRS), ISO TR9080, 97.5% LCL: 8.0 MPaThermal Conductivity, BS 874, 23°C: 0.4 W/m/°CVolume Resistivity, BS 2782:230A: >1e13 ohm-cmOxidation Induction Time, ISO TR10837, 200°C: >40 minOxidation Induction Time, ISO TR10837, 210°C: >20 min

Extrusion	Nominal Value	Unit
Melt Temperature	200 - 225	°C
Extrusion instructions		

Suggested Screen Pack: 40/80 Mesh

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

