

Evoprene™ COGEE 682

Styrene Ethylene Butylene Styrene Block Copolymer

AlphaGary

Message:

The Evoprene COGEE range was specially developed to provide materials which will comould or coextrude to engineering thermoplastics (ETPs). This enables, for example, polyamide (nylon) handles or ABS housings to be given a soft touch feel whilst polycarbonate lenses can have gaskets moulded on to provide a weathertight product.

The Evoprene COGEE grades are modified Kraton G based compounds. Many of the characteristics exhibited by the Evoprene G and Evoprene Super G ranges are shown by Evoprene COGEE compounds. However, they do have to be processed quite differently to obtain optimum bond strengths and performance characteristics.

General Information			
Features	Food Contact Acceptable		
	Good Weather Resistance		
	Ozone Resistant		
Uses	Soft Touch Applications		
Processing Method	Coextrusion		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ISO 2781
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	50		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	2.70	MPa	
300% Strain	5.50	MPa	
Tensile Stress (Yield)	11.0	MPa	ISO 37
Tensile Elongation (Break)	540	%	ISO 37
Tear Strength ¹	22	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	25	%	
70°C, 22 hr	76	%	
100°C, 22 hr	87	%	
Thermal	Nominal Value	Unit	
Service Temperature	-30 to 100	°C	
Bond Strength	1.00	MPa	Internal Method
M-S Flow	2.55	MPa	Internal Method
Ozone Resistance ² (35°C)	No Cracks		ISO 1431-1
UV Rating ³ (40°C)	No Visible Cracks or Crazing		

Injection	Nominal Value	Unit
Suggested Max Regrind	20	%
Rear Temperature	250 to 270	°C
Middle Temperature	250 to 270	°C
Front Temperature	250 to 270	°C
Nozzle Temperature	250 to 270	°C
Processing (Melt) Temp	190 to 220	°C
Mold Temperature	30.0 to 60.0	°C
Injection Rate	Fast	
Vent Depth	0.020 to 0.050	mm

NOTE

1. Method Ba, Angle (Unnicked)
2. 100 pphm/200 hrs/20% Strain
3. 350 hrs

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

