

RTP 300 SI 4

Polycarbonate

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Additive	Silicone lubricant (4%)		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2140	MPa	ASTM D638
Tensile Strength	51.7	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	530	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1600	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	132	°C	ASTM D648
CLTE - Flow	6.8E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.19	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	15	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.00		ASTM D150
Dissipation Factor (1 MHz)	0.010		ASTM D150
Arc Resistance	120	sec	ASTM D495
Additional Information			

Molding shrinkage, Linear-flow, ASTM D955, 0.25in: 10mil/inElongation at break, ASTM D638: 5-10%

Injection	Nominal Value	Unit
Rear Temperature	288 - 343	°C
Middle Temperature	288 - 343	°C
Front Temperature	288 - 343	°C
Mold Temperature	65.6 - 121	°C
Injection Pressure	103 - 138	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

