

LUVOCOM® TPE-0900 VP

Thermoplastic Elastomer

Lehmann & Voss & Co.

Message:

LUVOCOM®TPE-0900 VP is a thermoplastic elastomer (TPE) material, and the filler is carbon fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of TPE-0900 VP are:

Conductivity

Electrostatic protection

anti-warping

Wear-resistant

Typical application areas include:

engineering/industrial accessories

Automotive Industry

Handle

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Features	Conductivity		
	Low warpage		
	Electrostatic discharge protection		
	Good wear resistance		
Uses	Handle		
	Engineering accessories		
	Roller		
	Application in Automobile Field		
	Bearing		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183
Molding Shrinkage	0.40 - 0.80	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.50	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1500	MPa	ISO 527-2
Tensile Stress (Break)	38.0	MPa	ISO 527-2
Tensile Strain (Yield)	8.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1fU
Thermal	Nominal Value	Unit	Test Method

Continuous Use Temperature	80.0	°C	UL 746B
Maximum operating temperature-Short Term	110	°C	
Insulation Resistance		ohms	IEC 60167
Vicat Softening Temperature	180	°C	ISO 306/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+7	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying temperature-Hot air dryer, A	105	°C	
Drying time-Hot air dryer, A	3.0 - 4.0	hr	
Suggested Max Moisture	0.010	%	
Rear Temperature	200 - 220	°C	
Middle Temperature	210 - 230	°C	
Front Temperature	210 - 230	°C	
Nozzle Temperature	190 - 220	°C	
Processing (Melt) Temp	210	°C	
Mold Temperature	20.0 - 45.0	°C	

Injection instructions

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials. Lengthy dwell times for the melts in the cylinder should be avoided. Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing. The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets. Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very rapidly, originally sealed containers should only be opened immediately before processing. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT