## Wanthane® WHT-1295

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

## Message:

WHT-1295 is economical polyester-based TPU for injection molding and extrusion applications, supplied in form of transparent, translucent, colorless or slightly yellowish pellets with Good strength resilience

Applications:

Air Tube, Injection part. etc

General Information				
Features	Good Strength			
	Resilient			
Uses	Tubing			
Appearance	Colorless			
	Translucent			
	Transparent - Slight Yellow			
Forms	Pellets			
Processing Method	Extrusion			
	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	1.21	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	96		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress			ASTM D412	
100% Strain	12.0	МРа		
300% Strain	20.0	МРа		
Tensile Strength	32.0	МРа	ASTM D412	
Tensile Elongation (Break)	450	%	ASTM D412	
Tear Strength	140	kN/m	ASTM D624	
Thermal	Nominal Value	Unit	Test Method	
Glass Transition Temperature	-20.0	°C	ASTM D3417	
Injection	Nominal Value	Unit		
Drying Temperature	90.0 to 100	°C		
Drying Time	2.0 to 3.0	hr		
Rear Temperature	190	°C		
Middle Temperature	200	°C		
Front Temperature	205	°C		

Nozzle Temperature	210	°C
Injection Pressure	70.0	MPa
Extrusion	Nominal Value	Unit
Drying Temperature	90.0 to 100	°C
Drying Time	3.0 to 4.0	hr
Cylinder Zone 1 Temp.	190	°C
Cylinder Zone 3 Temp.	200	°C
Cylinder Zone 5 Temp.	205	°C
Die Temperature	200	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

