

# Di-Pak™ R-4525/17

Thermoplastic

Hapco Inc.

## Message:

RIGID

DI-PAK R-4525 Series

A general purpose series of low viscosity, strong, potting and encapsulating compounds. DI-PAK R-4525 has excellent electrical insulating properties and bonds well to many substrates. By varying the curing agents, the desired cure and working life can be obtained.

General Information			
Features	Electrically Insulating		
	Good Processability		
	Good Toughness		
	High Heat Resistance		
	High Strength		
	Low Viscosity		
Uses	Battery Cases		
	Electrical/Electronic Applications		
	Power Cable Shields		
	Switches		
Appearance	Black		
Forms	Liquid		
Processing Method	Encapsulating		
	Potting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm <sup>3</sup>	ASTM D4669
Molding Shrinkage - Flow	0.050 to 0.10	%	ASTM D2566
Weight - per cubic inch	23	g	
Service Temperature	75	°C	
Gel Time <sup>1</sup> (25°C)	40.0 to 60.0	min	ASTM D2971
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2480	MPa	ASTM D638
Tensile Strength	56.9	MPa	ASTM D638
Tensile Elongation (Break)	3.8	%	ASTM D638
Flexural Modulus	2670	MPa	ASTM D790
Flexural Strength	65.2	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	34	J/m	ASTM D256
Unnotched Izod Impact	41	J/m	ASTM D256
Thermal	Nominal Value	Unit	
Thermal Conductivity	0.40	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.9E+12	ohms·cm	ASTM D257
Dielectric Strength	23	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	3.40		
100 kHz	3.30		
Dissipation Factor (25°C, 100 kHz)	0.023		ASTM D150
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 100, Mix Ratio by Volume: 100		
Part B	Mix Ratio by Weight: 24, Mix Ratio by Volume: 40		
Thermoset Mix Viscosity (25°C)	1800	cP	ASTM D4878
Demold Time (21°C)	1400	min	
NOTE			
1.	100 g		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

