

# Clyrell RC549S

Polypropylene Random Copolymer

LyondellBasell Industries

Message:

Clyrell RC549S is a development polypropylene resin with nucleation and antistatic additivation designed for injection molding. It features an excellent combination of high stiffness, high transparency and good impact strength that enables customers to achieve excellent organoleptic performance and a superior aesthetic appearance which appeals to end users. The product contains the most advanced clarifier system that allows easy processing at significantly lower temperatures than similar resins, which customers report enables them to reduce cycle times to save energy and improve productivity. It is not intended for medical and pharmaceutical applications.

General Information			
Additive	Nucleating agent		
	Clarifier		
	Antistatic property		
Features	Excellent Organoleptic Properties		
	Nucleated		
	Rigidity, high		
	Antistatic property		
	Impact resistance, good		
	Fast molding cycle		
	Definition, high		
	Good appearance		
Uses	Household goods		
	Container		
	Sporting goods		
	Toys		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	44	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant (23°C)	1470	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	34.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield, 23°C	11	%	ISO 527-2/50
Fracture, 23°C	> 50	%	ISO 527-2/50
Flexural Modulus - Secant <sup>1</sup> (23°C)	1450	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
0°C	1.2	kJ/m <sup>2</sup>	ISO 179
23°C	2.5	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	86.0	°C	ISO 75-2/B
Optical	Nominal Value	Unit	Test Method
Gloss (60°)	128		ASTM D2457
Haze (1000 μm)	10	%	ASTM D1003
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 - 230	°C	
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

