

# Medalist™ MD-12150 XRD (PRELIMINARY DATA)

Thermoplastic Elastomer  
Teknor Apex Company

**Message:**

Medalist MD-12150 XRD is designed for medical and healthcare applications requiring high elasticity and tensile strength. Medalist MD-12150 XRD is a translucent grade, can be sterilized and is suitable for injection molding and extrusion. This grade also exhibits excellent adhesion to polypropylene. Every ingredient used to formulate this product is either "generally recognized as safe" (GRAS), prior sanctioned, subject to an effective Food Contact Notification (FCN), subject to a Threshold of Regulation (TOR) or identified in one or more sections of Title 21 of the code of Federal Regulations published by the US FDA.

General Information	
Features	Low Specific Gravity
	Without Fillers
	Low density
	smoothness
	Low liquidity
	Medium hardness
Uses	Drug
	Medical/nursing supplies
Agency Ratings	ISO 10993 Part 5
Appearance	Translucent
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	4.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	50		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Across Flow (100% Strain)	0.870	MPa	ISO 37
Tensile Stress - Across Flow (Break)	6.80	MPa	ISO 37
Tensile Elongation - Across Flow (Break)	840	%	ISO 37
Tear Strength <sup>1</sup>			ISO 34-1
Transverse flow	11	kN/m	ISO 34-1
Flow	19	kN/m	ISO 34-1

Compression Set <sup>2</sup> (70°C, 22 hr)	25	%	ISO 815
Injection	Nominal Value	Unit	
Rear Temperature	160 - 177	°C	
Middle Temperature	182 - 204	°C	
Front Temperature	193 - 216	°C	
Nozzle Temperature	182 - 227	°C	
Processing (Melt) Temp	182 - 227	°C	
Mold Temperature	26.7 - 48.9	°C	
Injection Rate	Moderate-Fast		
Back Pressure	0.172 - 0.689	MPa	
Screw Speed	50 - 100	rpm	
Cushion	3.81 - 12.7	mm	

#### Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

#### NOTE

1. Method B, right-angle specimen  
(without cut)
2. Type a

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT