

# ADREF® O05NOEGD01V2

Polypropylene Copolymer

A.D. Compound S.p.A.

Message:

PP Stabilized Copolymer Black No filled - Flame Retardant

General Information			
Recycled Content	Yes		
Features	Copolymer		
	Flame retardancy		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	23	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1000 - 1300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.5 - 8.0	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	80.0	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

