

KumhoSunny PBT 3740G

Polybutylene Terephthalate

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

PBT3740G is heat resistance property and low smell PBT resin. PBT3740G has high rigidity, high tenacity and excellent UV stability. PBT3740G is mainly used in automobile air condition vent, shutter, microwave oven, etc.

General Information			
Features	Good UV Resistance		
	High Rigidity		
	Low to No Odor		
	Medium Heat Resistance		
Uses	Automotive Applications		
UL File Number	E254819		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.55	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	120	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	10000	MPa	ASTM D790
Flexural Strength	185	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	217	°C	
1.8 MPa, Unannealed	210	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
2.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	120 to 140	°C	

Drying Time	4.0 to 6.0	hr
Processing (Melt) Temp	220 to 260	°C
Mold Temperature	50.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

