

Gallonprene® GP210-8009

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

Message:

Gallonprene® GP210-8009 is a thermoplastic elastomer (TPE) product. It can be processed by extrusion, profile extrusion or injection molding, and is available in Africa and the Middle East, Latin America or the Asia-Pacific region. Gallonprene® GP210-8009 applications include wires and cables, engineering/industrial accessories and hoses.

Features include:

Comply with REACH standard

ROHS certification

Halogen-free

| General Information | | | |
|---|---|-------------------|-------------|
| Features | Halogen-free | | |
| Uses | O-rings overmolding Wire and cable applications Pipe fittings Profile | | |
| Agency Ratings | EC 1907/2006 (REACH) | | |
| RoHS Compliance | RoHS compliance | | |
| Appearance | Translucent Rough surface polishing | | |
| Processing Method | Extrusion Profile extrusion molding Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.878 | g/cm ³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (200°C/10.0 kg) | 3.5 | g/10 min | ASTM D1238 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 23°C) | 80 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (Break) | 13.0 | MPa | ASTM D412 |
| Tensile Elongation ² (Break) | 700 | % | ASTM D412 |
| Injection | Nominal Value | Unit | |
| Rear Temperature | 200 - 220 | °C | |
| Middle Temperature | 210 - 230 | °C | |
| Front Temperature | 220 - 240 | °C | |

| | | |
|---|---------------|------|
| Processing (Melt) Temp | 180 - 200 | °C |
| Mold Temperature | 30.0 - 60.0 | °C |
| Injection Rate | Fast | |
| Injection instructions | | |
| Processing Temperature Limit: 280°CInjection Pressure: HighBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 210 to 230°CCenter Temperature: 220 to 240°CFront Temperature: 230 to 250°C Melt Temperature: 180 to 200°C Mold Temperature: 30 to 60°CProcessing Temperature Limit: 280°CInjection Pressure: HighInjection Speed: HighBack Pressure: 20 to 50% | | |
| Extrusion | Nominal Value | Unit |
| Cylinder Zone 1 Temp. | 160 - 180 | °C |
| Cylinder Zone 2 Temp. | 170 - 190 | °C |
| Cylinder Zone 3 Temp. | 180 - 200 | °C |
| NOTE | | |
| 1. | 500 mm/min | |
| 2. | 500 mm/min | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

