

# Magnobond 6289

Epoxy; Epoxide  
Magnolia Plastics, Inc.

Message:

Magnobond 6289 is an Epoxy; Epoxide (Epoxy) product. It is available in North America. Applications of Magnobond 6289 include adhesives/tapes and sealing applications.  
Characteristics include:  
Chemical Resistant  
Heat Resistant

General Information			
Features	Good Chemical Resistance		
	High Heat Resistance		
	Solvent Resistant		
Uses	Adhesives		
	Sealants		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm <sup>3</sup>	ASTM D792
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.9E+14	ohms·cm	ASTM D257
Dielectric Strength (0.00318 mm)	28	kV/mm	ASTM D149
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Hardener	Mix Ratio by Weight: 32		
Resin	Mix Ratio by Weight: 100		
Pot Life (24°C)	18	min	
Thermoset Mix Viscosity (24°C)	40000	cP	ASTM D2393
Demold Time (24°C)	120 to 360	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT