

# KumhoSunny ABS HGX4400

Acrylonitrile Butadiene Styrene  
Shanghai KumhoSunny Plastics Co., Ltd.

Message:  
HGX4400 is Injection grade ABS resin with heat resistance property.HGX4400 is mainly used in instrument panel, radiator grille, hair dryer, coffee pot, etc.

General Information			
Features	Medium Heat Resistance		
Uses	Automotive Applications		
	Consumer Applications		
	Electrical/Electronic Applications		
	Household Goods		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	3.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	46.0	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	2200	MPa	ASTM D790
Flexural Strength	62.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	110	°C	ASTM D648
Vicat Softening Temperature	120	°C	ASTM D1525 <sup>1</sup>
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+14	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 95.0	°C	

Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	< 0.050	%
Rear Temperature	220 to 240	°C
Middle Temperature	230 to 250	°C
Front Temperature	240 to 260	°C
Nozzle Temperature	250 to 270	°C
Processing (Melt) Temp	240 to 260	°C
Mold Temperature	50.0 to 80.0	°C
Back Pressure	1.00 to 5.00	MPa
Screw Speed	30 to 70	rpm

NOTE

1. Rate B (120°C/h)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT