

Dryflex® SE 90A001N U

Styrene Ethylene Butylene Styrene Block Copolymer

ELASTO

Message:

Dryflex SE 90A001N U: Thermoplastic Elastomer

Base Material: TPS-SEBS

Hardness: 90 Shore A

Service Temperature Range: -50 to +125°C (Unstressed Material)

Colour: Translucent, but can easily be coloured in any shade

Presentation: Free flowing pellets that can be processed without predrying when stored under normal conditions

Weather Resistance: Excellent

Ozone / UV Resistance: Excellent

Chemical Resistance: Good (Excluding organic solvents, aromatic and vegetable oils)

Recycling: 100% Recyclable

Mould Shrinkage: Approximately 0.75 - 2% depending on shape of the detail and placement of the gate

Bonds to: PP, PE

General Information			
Features	Good UV resistance		
	Recyclable materials		
	Ozone resistance		
	Good chemical resistance		
	Good weather resistance		
Appearance	Translucent		
	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.890	g/cm³	ISO 2781
Molding Shrinkage ¹	0.75 - 2.0	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	90		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Across Flow			ISO 37
100% strain	4.90	MPa	ISO 37
300% strain	6.00	MPa	ISO 37
Tensile Stress - Across Flow (Yield)	15.2	MPa	ISO 37
Tensile Elongation - Across Flow (Break)	750	%	ISO 37
Tear Strength - Across Flow ²	51	kN/m	ISO 34-1
Compression Set ³			ISO 815
23°C, 72 hr	41	%	ISO 815
70°C, 22 hr	61	%	ISO 815

100°C, 22 hr	76	%	ISO 815
Thermal	Nominal Value	Unit	
Service Temperature	-50 - 125	°C	
Injection	Nominal Value	Unit	
Rear Temperature	180 - 210	°C	
Middle Temperature	180 - 210	°C	
Front Temperature	180 - 210	°C	
Mold Temperature	15 - 50	°C	
NOTE			
1.	Depending on shape of the detail and placement of the gate.		
2.	C method: crescent sample		
3.	Type B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

