

LNP™ LUBRICOMP™ LL004C compound

Polyetheretherketone
SABIC Innovative Plastics

Message:

LNP LUBRICOMP LL004C is a compound based on Polyetheretherketone resin containing PTFE. Added features of this material include: Internally Lubricated, Clean Compounding System.
Also known as: LNP* LUBRICOMP* Compound LL-4040 CCS
Product reorder name: LL004C

General Information			
Additive	PTFE lubricant		
Features	Low (to None) Ion Content		
	Lubrication		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	1.3	%	ASTM D955
Transverse flow: 24 hours	1.9	%	ASTM D955
Vertical flow direction: 24 hours	1.9	%	ISO 294-4
Flow direction: 24 hours	1.3	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2900	MPa	ASTM D638
--	3070	MPa	ISO 527-2/1
Tensile Strength			
Yield	74.5	MPa	ASTM D638
Yield	73.0	MPa	ISO 527-2
Fracture	69.6	MPa	ASTM D638
Fracture	69.0	MPa	ISO 527-2
Tensile Elongation			
Yield	5.8	%	ASTM D638
Yield	5.0	%	ISO 527-2
Fracture	23	%	ASTM D638
Fracture	12	%	ISO 527-2
Flexural Modulus			
--	2960	MPa	ASTM D790
--	3320	MPa	ISO 178
Flexural Strength			
--	117	MPa	ASTM D790
--	118	MPa	ISO 178

Coefficient of Friction		ASTM D3702 Modified	
With self-dynamics	0.52	ASTM D3702 Modified	
With Self-Static	0.43	ASTM D3702 Modified	
Wear Factor - Washer	128	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	96	J/m	ASTM D256
23°C ²	8.8	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1500	J/m	ASTM D4812
23°C ³	91	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	3.00	J	ASTM D3763
--	1.00	J	ISO 6603-2
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

