# POLYTROPE® STR 1060EU-01 NATURAL

## **Enhanced TPO Polyolefin**

A. Schulman Inc.

General Information

#### Message:

POLYTROPE STR 1060EU resin is a high melt strength thermoformable TPO that balances toughness and exceptionally high stiffness, enabling processors and end users to reduce product weight and improve processing efficiency without sacrificing product performance. It can be extruded in smooth or textured surfaces, or co-extruded with a POLYTROPE STR enhanced polyolefin cap resin to further customize its' durability, appearance, or feel for interior and exterior applications. The capability of POLYTROPE STR 1060EU to provide an exceptionally smooth surface in extrusion and thermoforming makes it well suited to lamination processes with decorative films. It is also easily colored and is paintable by standard TPO paint systems.

General information				
Features	Good Melt Strength			
	Good Weather Resistance			
	Low CLTE			
	Low Temperature Impact Resistance			
	Paintable			
	Recyclable Material			
Forms	Pellets			
Processing Method	Coextrusion			
	Extrusion			
	Profile Extrusion			
	Sheet Extrusion			
	Thermoforming			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity <sup>1</sup>	1.16	g/cm³	ISO 1183	
Melt Mass-Flow Rate (MFR) (230°C/2.16				
kg)	0.70	g/10 min	ISO 1133	
Molding Shrinkage (23°C, 24 hr, 3.18 mm)	0.70 to 0.90	%	ISO 294-4	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress <sup>2</sup> (Yield, 23°C)	30.8	MPa	ISO 527-2	
Tensile Strain <sup>3</sup> (Break, 233°C)	180	%	ISO 527-2	
Flexural Modulus - Chord <sup>4</sup> (23°C)	4000	MPa	ISO 178	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact - Flow			ASTM D256	
-30°C, 3.18 mm, Injection Molded	32	J/m		
23°C, 3.18 mm, Injection Molded	370	J/m		
Instrumented Dart Impact (4°C, Total Energy, Ductile Failure)	40.7	J	ASTM D3763	

Heat Deflection Temperature (0.45 MPa,			
Unannealed)	117	°C	ISO 75-2/Bf
CLTE - Flow (-30 to 100°C)	5.4E-5	cm/cm/°C	ASTM E831
Flammability	Nominal Value		Test Method
Flame Rating (3.18 mm, All Colors)	НВ		UL 94
Optical	Nominal Value		Test Method
Gardner Gloss (60°, 3180 μm,			
Thermoformed, Smooth)	20 to 40		ISO 2813
Additional Information	Nominal Value	Unit	Test Method
Additional Information	Norminal value	Offic	rest Metriod
Heat Sag - 8 inch span, two point support	Norminal value	Offic	rest Method
	0.00	mm	ASTM D3769
Heat Sag - 8 inch span, two point support			
Heat Sag - 8 inch span, two point support (149°C, 3.20 mm)			
Heat Sag - 8 inch span, two point support (149°C, 3.20 mm)  NOTE	0.00		
Heat Sag - 8 inch span, two point support (149°C, 3.20 mm)  NOTE  1.	0.00 Method A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

