

Stat-Tech™ AS-1000 AS Amber

Acrylonitrile Butadiene Styrene

PolyOne Corporation

Message:

Stat-Tech™ Electrically Conductive Compounds are specifically engineered to provide anti-static, ESD and RFI/EMI shielding performance for critical electronic equipment applications. These compounds combine the performance of select engineering resins with reinforcing additives such as carbon powder, carbon fiber, nickel-coated carbon fiber and stainless steel fiber, for low to high levels of conductivity depending upon application requirements.

General Information			
Features	Antistatic		
	Non-Sloughing		
Uses	Aerospace Applications		
	Automotive Electronics		
	Business Equipment		
	Computer Components		
	Connectors		
	Electrical Housing		
	Electrical/Electronic Applications		
	Housings		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	35.0	MPa	ASTM D638
Flexural Modulus	20700	MPa	ASTM D790
Flexural Strength	59.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	160	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	87.0	°C	
1.8 MPa, Unannealed, 6.35 mm	74.0	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9 to 1.0E+12	ohms	ASTM D257
Volume Resistivity	1.0E+9 to 1.0E+12	ohms · cm	ASTM D257


Static Decay		
(Mil-B-81705C), 12% RH, 5000 kV to 50 kV	0.3	sec
(Mil-B-81705C), 50% RH, 5000 kV to 50 kV	0.1	sec
Injection	Nominal Value	Unit
Processing (Melt) Temp	227 to 238	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT