

TRIMID® N66-G13LU

Polyamide 66

Polymer Technology and Services, LLC

Message:

TRIMID® N66-G13LU is a Polyamide 66 (Nylon 66) product filled with 13% glass fiber. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: lubricated.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Ultimate)	107	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	4480	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.17 mm)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	243	°C	ASTM D648
Melting Temperature	254	°C	
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	4.0	hr	
Rear Temperature	254	°C	
Middle Temperature	268	°C	
Front Temperature	285	°C	
Nozzle Temperature	266 to 282	°C	
Processing (Melt) Temp	271 to 293	°C	
Mold Temperature	26.7 to 93.3	°C	
Injection Pressure	68.9	MPa	
Back Pressure	0.0689 to 0.689	MPa	
Screw Speed	30 to 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

