

SILVER® SA-1105

Styrene Butadiene Styrene Block Copolymer
Guangdong Silver Age Sci & Tech. Co., Ltd

Message:

SILVER® SA-1000 elastomer is a kind of thermoplastic elastomer comprising of unsaturated styrene—butadiene rubber for indoor room temperature applications, such as toys, clear product, bearing seals and sole, which is similar to thermoset rubber in physical properties. And SA—1000 elastomer can be injected or extruded on thermoplastic equipment.

SA—1000 Elastomer (Unsaturated Styrene—butadiene Rubber)

Characteristics:
similar to thermoset rubber in physical properties

Applications:
toys, seal ring, cushion blocking, insole, sole, fender board, cap of pen, truckle, tire and so on

General Information	
Features	Copolymer
Uses	Caps
	Footwear
	Seals
	Tires
	Toys
Appearance	Clear/Transparent
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (130°C/2.16 kg)	49	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 3 sec)	25		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	0.800	MPa	ASTM D638
Tensile Elongation ² (Break)	> 600	%	ASTM D638
Injection	Nominal Value	Unit	
Processing (Melt) Temp	130 to 170	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	130 to 170	°C	
NOTE			
1.	500 mm/min		
2.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

