

ALTECH® ABS A 1000/627 UV

Acrylonitrile Butadiene Styrene

ALBIS PLASTIC GmbH

Message:

ALTECH® ABS A 1000/627 UV is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America.

Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- Heat Stabilizer
- Low Emissions

General Information			
Additive	Heat Stabilizer		
	Processing Stabilizer		
	UV Stabilizer		
Features	Good Flow		
	Heat Stabilized		
	Low Emissions		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	20.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2350	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	50.0	MPa	
--	45.0	MPa	
Tensile Strain			ISO 527-2
Yield	3.0	%	
Break	7.0	%	
Flexural Modulus	2380	MPa	ISO 178
Flexural Stress			ISO 178
--	75.0	MPa	
3.5% Strain	72.0	MPa	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA

--	12	kJ/m ²	
-40°C	5.0	kJ/m ²	
-20°C	6.0	kJ/m ²	
Charpy Unnotched Impact Strength	No Break	ISO 179/1eU	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	105	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		
1.50 mm	HB		
3.00 mm	HB		
Glow Wire Flammability Index			IEC 60695-2-12
1.00 mm	650	°C	
2.00 mm	650	°C	
3.00 mm	650	°C	
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	80.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
Circulation Dryer	3.0 to 6.0	hr	
Desiccant Dryer	2.0 to 4.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	50.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT