

Epoxies, Ect. 20-2390

Polyurethane
Epoxies, Etc.

Message:

This two component urethane series are low durometer (30-90 Shore A), potting, casting, and encapsulating compounds. They are unfilled materials engineered to provide excellent hydrolytic stability and low moisture permeability. They have outstanding thermal cycling properties, low glass transition temperatures and low embedment stress to sensitive electronic components.

These unique urethane formulations maintain their integrity over a wide operating temperature range. The low glass transition temperature of approximately -70°C makes these urethanes ideal for low temperature potting applications. These systems exhibit very little hardness increase when cooled to -72°C.

- Features:
- Maintains flexibility at low temperatures
 - Thermal cycling stability
 - Excellent electrical insulation
 - Chemical resistance
 - Low stress on sensitive components
 - Hydrolytic stability

General Information		
Features	Electrically Insulating	
	Good Chemical Resistance	
	Good Flexibility	
	Hydrolytically Stable	
	Low to No Water Absorption	
Uses	Electrical/Electronic Applications	
Appearance	Black	
Processing Method	Casting	
	Encapsulating	
	Potting	
Thermal	Nominal Value	Unit
Glass Transition Temperature	-70.0	°C
CLTE - Flow	2.3E-4	cm/cm/°C
Electrical	Nominal Value	Unit
Surface Resistivity	1.0E+16	ohms
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	3200	cP
Additional Information	Nominal Value	Unit
Operating Temperature	-40.0 to 125	°C
Uncured Properties	Nominal Value	Unit
Color	Black	
Mix Ratio by Weight (PBW)		
Part A	100	

Part B	40	
Density		
25°C ¹	0.898	g/cm ³
25°C ²	1.20	g/cm ³
Curing Time		
85°C	0.66	hr
65°C	1.5	hr
45°C	2.5	hr
25°C	24 to 48	hr
Pot Life ³ (25°C)	40	min
Cured Properties	Nominal Value	Unit
Shore Hardness (Shore A)	90	
Tensile Strength	7.52	MPa
Tensile Elongation at Break	260	%
Relative Permittivity (1 kHz, 25°C)	4.50	
Volume Resistivity	6.0E+16	ohms · cm
NOTE		
1.	Part A	
2.	Part B	
3.	100 gram mass	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

