

# KPOL-PP K-PPH 11.0

Polypropylene Homopolymer  
KPOL Chem Co.

Message:

Polypropylene Homopolymer  
Applications  
The KPOL® is a homopolymer used for general purpose injection moulding applications  
It is suitable for production of complex articles with long flow paths and thin walls. Typical applications are closures and garden furniture.  
Characteristics  
The KPOL® is specially developed for producing rigid injection molded articles for general purpose applications. It gives consistent processability and high gloss at the products. It is a controlled rheology grade.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Controlled Rheology		
	Food Contact Acceptable		
	Good Processability		
	High Gloss		
Uses	Homopolymer		
	Closures		
	Furniture		
	General Purpose		
	Thin-walled Parts		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	72		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	36.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant	1550	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	28	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	102	°C	ASTM D648
Vicat Softening Temperature	150	°C	ASTM D1525 <sup>3</sup>
NOTE			
1.	Type IV, 50 mm/min		
2.	Type IV, 50 mm/min		
3.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

