

Elastollan® C 95 A

Thermoplastic Polyurethane Elastomer (Polyester)

BASF Polyurethanes GmbH

Message:

Thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties. Outstanding tensile strength and high elongation at break, good damping characteristics, a high resilience performance and very good wear resistance.

Typical applications

Spiral tubing, pneumatic tubing, round belting, technical mouldings e.g. bushes, dust caps, seals, joints, blow moulded bellows, fan belts.

General Information			
UL YellowCard	E140250-100728234		
Features	Good Wear Resistance		
	High Elongation		
	High Tensile Strength		
	Resilient		
Uses	Belts/Belt Repair		
	Bushings		
	Caps		
	Seals		
	Tubing		
Processing Method	Blow Molding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 7619
Shore A, 3 sec	96		
Shore D, 3 sec	47		
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	25.0	mm ³	ISO 4649-A
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			DIN 53504
20% Strain	8.00	MPa	
100% Strain	11.0	MPa	
300% Strain	22.0	MPa	
Tensile Stress			DIN 53504
Yield ¹	40.0	MPa	

Yield	55.0	MPa	
Tensile Elongation			DIN 53504
Break ²	500	%	
Break	550	%	
Tear Strength ³	120	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	30	%	
70°C, 24 hr	45	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	170 to 240	°C	
Mold Temperature	20.0 to 70.0	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	150 to 230	°C	
NOTE			
1.	after storage in water for 21 days at 80°C		
2.	after storage in water for 21 days at 80°C		
3.	Method Bb, Angle (Nicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT