

Padermid 6 AF

Polyamide 6
TKC Kunststoffe e.K.

Message:

Padermid 6 AF is a Polyamide 6 (Nylon 6) material. It is available in Europe for injection molding.

Typical applications include:

- Automotive
- Consumer Goods
- Handles

General Information			
Uses	Automotive Applications		
	Consumer Applications		
	Handles		
Appearance	Black		
	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Molding Shrinkage			ISO 2577
Across Flow	1.3	%	
Flow	0.90	%	
Water Absorption (23°C, 24 hr)	1.5	%	DIN 53495
Viscosity	3.10		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ISO 527-2/1
Tensile Stress (Yield)	80.0	MPa	ISO 527-2/50
Tensile Strain (Break)	15	%	ISO 527-2/50
Flexural Modulus ¹	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	180	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	°C	ISO 75-2/A
Vicat Softening Temperature	206	°C	ISO 306
Melting Temperature (DSC) ²	220	°C	ISO 3146
Injection	Nominal Value	Unit	

Drying Temperature	80.0	°C
Drying Time	4.0	hr
Processing (Melt) Temp	260 to 280	°C
Mold Temperature	70.0 to 90.0	°C
Injection Pressure	70.0 to 120	MPa

NOTE

1. 2.0 mm/min
2. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

