

TORZEN Marathon™ FRU4800XHL NC01

Polyamide 66
INVISTA Engineering Polymers

Message:

TORZEN Marathon™ FRU4800XHL NC01 is a flame retardant and heat stabilized Polyamide 66 resin suitable for injection molding. It does not contain elemental bromine, phosphorus or heavy metals.

General Information			
UL YellowCard	E333734-101430494		
Additive	Heat Stabilizer		
Features	Bromine Free		
	Flame Retardant		
	Good Processability		
	Heat Stabilized		
	Low (to None) Phosphorus Content		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	1.3 to 1.6	%	
Flow : 2.00 mm	1.3 to 1.6	%	
Water Absorption (23°C, 24 hr)	1.8	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3700	MPa	ISO 527-2/1
Tensile Stress (Break)	80.0	MPa	ISO 527-2
Tensile Strain (Break)	13	%	ISO 527-2
Flexural Stress	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.4	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	140	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	85.0	°C	ISO 75-2/A
Melting Temperature	263	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method

Comparative Tracking Index (CTI) (3.00 mm)	600	V	UL 746
Comparative Tracking Index (CTI) (3.00 mm)	PLC 0		ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94, IEC 60695-11-10, -20
0.400 mm	V-0		
0.800 mm	V-0		
1.50 mm	V-0		
3.00 mm	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
0.400 mm	960	°C	
0.800 mm	960	°C	
1.50 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.400 mm	990	°C	
0.800 mm	990	°C	
1.50 mm	990	°C	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.080 to 0.18	%	
Rear Temperature	250 to 270	°C	
Middle Temperature	260 to 280	°C	
Front Temperature	270 to 280	°C	
Nozzle Temperature	270 to 280	°C	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	50.0 to 90.0	°C	
Back Pressure	0.200 to 1.00	MPa	
Screw Speed	75 to 180	rpm	
Cushion	4.00 to 6.00	mm	
Vent Depth	7.0E-3 to 0.040	mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT