

PETOPLEN FH 360

Polypropylene
PETKIM Petrokimya Holding A.S.

Message:
Application: BOPP film, woven bags, rope, flat tape and monofilament

General Information			
Uses	Film		
	Monofilaments		
	Rope		
	Tape		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.1 to 4.1	g/10 min	ASTM D1238
Color - b-value (10D65)	1.8		Internal Method
Contamination - 100g	< 10	pcs	Internal Method
Fish Eye	< 11.0	pcs/g	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	35.0	MPa	
Break	40.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT