Propafilm™ RDP125

Polypropylene Alloy

Innovia Films Ltd.

Message:

Peelable Seal Differentially Barrier Coated Film

Biaxially oriented polypropylene (BOPP) film coated on one side with an aqueous dispersion of polyvinylidene chloride (PVdC) copolymer, the other side coated with an aqueous acrylic dispersion.

RDP125 is recommended for use in plain and printed packs. Applications in the cookie, bakery and confectionery industries. Particulally suitable for V.F.F applications.

General Information				
Features	Excellent Printability	Excellent Printability		
	Food Contact Acceptable			
	Good Impact Resistance			
	Heat Sealable			
	Low Moisture Vapor Transmission			
	Low Temperature Impact Resistance			
	Puncture Resistant			
Uses	Bi-axially Oriented Film			
	Food Service Applications			
	Laminates			
	Packaging			
Forms	Film			
Physical	Nominal Value	Unit	Test Method	
Molding Shrinkage			Internal Method	
Flow: 121°C, 1 min	4.0	%		
Flow: 129°C, 1 min	7.0	%		
Across Flow: 129°C, 1 min	1.0	%		
Mechanical	Nominal Value	Unit	Test Method	
Coefficient of Friction			ASTM D1894	
vs. Itself - Dynamic, Outside/Outside	0.25			
vs. Itself - Static, Outside/Outside	0.25			
Films	Nominal Value	Unit	Test Method	
Film Thickness - Tested	3200	μm		
Seal Strength			Internal Method	
1	0.12	N/mm		
2	0.14	N/mm		
Seal Initiation Temperature			Internal Method	
3	85.0 to 146	°C		

⁴	104 to 146	°C		
Oxygen Permeability (25°C, 0% RH)	0.74	cm³·mm/m²/atm/24 hr	ASTM F1927	
Water Vapor Transmission Rate (38°C, 90	%			
RH)	4.0	g/m²/24 hr	ASTM F1770	
Yield	34.9	m²/kg	Internal Method	
Optical	Nominal Value	Unit	Test Method	
Gloss (45°)	100		ASTM D2457	
Haze ⁵	3.5	%	ASTM D1003	
NOTE				
1.	Acrylic/Acrylic; 265°F; 2secs; 15psi			
2.	PVdC/PVdC; 265°F; 2secs; 15psi			
3.	Acrylic/Acrylic; 2secs; 15psi			
4.	PVdC/PVdC; 2secs; 15psi			
5.	Wide angle; 2.5°			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

