

Huaфон JF-D-8603

Polyurethane
Huaфон Group Co., Ltd.

Message:
PU Resin for Dry-Process Surface Layer
Characteristics and Application
Smooth, soft, full of feeling, heat resistance, good abrasion resistance, nonstick surface.

General Information		
Features	Good Abrasion Resistance	
	Medium Heat Resistance	
	Non-Stick	
	Soft	
Appearance	Milky White	
	Translucent	
Forms	Liquid	
Physical	Nominal Value	
pH	7.0 to 9.0	
Solvents	Water	
Uncured Properties	Nominal Value	Unit
Solids Content	29 to 31	%
Viscosity (25°C)	1.5 to 3.0	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	2.50 to 3.50	MPa
Tensile Strength	> 20.0	MPa
Tensile Elongation at Break	> 450	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT