

# Geon™ BIO HC5165G

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

A flexible vinyl formulated to achieve a minimum level of 25% bio-based content and classified as a PolyOne Sustainable Solution

General Information	
Features	Non-Phthalate Plasticizer
	Renewable Resource Content
Uses	Connectors
	Medical/Healthcare Applications
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>			ASTM D638
Break	10.0	MPa	
100% Strain	4.00	MPa	
Tensile Elongation <sup>2</sup> (Break)	390	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-33.3	°C	ASTM D746
Injection	Nominal Value	Unit	
Processing (Melt) Temp	182 to 188	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	177 to 182	°C	

NOTE	
1.	510 mm/min
2.	510 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

