

ELASTOSIL® N 288

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1

Gaskets, Mechanical and Plant Engineering

Bonding & Sealing, Adhesives and Sealants

Small Appliances, Household Appliances

Heating and Air Conditioning, Mechanical and Plant Engineering

Heating and Air Conditioning, Household Appliances

General Information			
Uses	Adhesives		
	Bonding		
	Sealants		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Red		
Density			
--	1.08	g/cm ³	DIN 53479
--	1.09	g/cm ³	ISO 1183
Viscosity	65	Pa · s	Brookfield
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	35		DIN 53505
Tensile Strength	3.20	MPa	DIN 53504
Tensile Elongation at Break	350	%	DIN 53504
Tear Strength	5.00	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT