

Laticonther 52/11 CP3/600 F3

Polypropylene Homopolymer

LATI S.p.A.

Message:

High thermal conductivity product based on Polypropylene homopolymer (PPh).
Special filler. Potentially suitable for food/medical contact application.

General Information			
Filler / Reinforcement	Filler		
Features	Homopolymer		
	Thermally Conductive		
Uses	Medical/Healthcare Applications		
	Non-specific Food Applications		
Physical	Nominal Value	Unit	Test Method
Density	1.43	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.90 to 1.4	%	
Flow : 2.00 mm	0.90 to 1.4	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4700	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	20.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	1.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	1.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	130	°C	ISO 75-2/B
1.8 MPa, Unannealed	100	°C	ISO 75-2/A
Vicat Softening Temperature	115	°C	ISO 306/B50
Thermal Conductivity	4.0	W/m/K	Internal Method
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	230 to 250	°C	
Mold Temperature	30.0 to 60.0	°C	

Injection Rate	Moderate
NOTE	
1.	60 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT