Topilene® R530A

Polypropylene Homopolymer

Hyosung Corporation

Message:

Characteristics: Transparency FDA DMF 21499 USP Class VI EP 3.1.6 Applications: IV bottle

General Information			
Additive	High Slip		
Features	High Clarity		
	Homopolymer		
Uses	Medical Devices		
	Medical/Healthcare Applications		
Agency Ratings	DMF 21499		
	EP Monograph 3.1.6		
	FDA Unspecified Rating		
	USP Class VI		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	2.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	932	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	78	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

