

Novamid® 1010CH1

Polyamide 6

DSM Engineering Plastics

Message:

Novamid® 1010CH1 is a Polyamide 6 (Nylon 6) material. It is available in Asia Pacific for injection molding.

Important attributes of Novamid® 1010CH1 are:

Flame Rated

Low Viscosity

General Information				
Features		Low Viscosity		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	2.8	--	%	ISO 62
Viscosity Number	118	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3100	1000	MPa	ISO 527-2
Tensile Stress (Yield)	80.0	40.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	22	%	ISO 527-2
Nominal Tensile Strain at Break	28	> 50	%	ISO 527-2
Flexural Modulus	2900	880	MPa	ISO 178
Flexural Stress	115	40.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	31	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	168	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	58.0	--	°C	ISO 75-2/A
Melting Temperature ¹	220	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	7.0E-5	--	cm/cm/°C	
Transverse	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	2.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	--	ohms · cm	IEC 60093
Electric Strength	27	--	kV/mm	IEC 60243-1

Relative Permittivity (1 MHz)	4.00	--		IEC 60250
Dissipation Factor (1 MHz)	0.023	--		IEC 60250
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	V-2	--		IEC 60695-11-10, -20
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	230 to 235		°C	
Middle Temperature	235 to 250		°C	
Front Temperature	240 to 260		°C	
Nozzle Temperature	240 to 270		°C	
Processing (Melt) Temp	240 to 275		°C	
Mold Temperature	50.0 to 80.0		°C	
Injection Rate	Moderate-Fast			
Back Pressure	3.00 to 10.0		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT