

ALKAMIX™ MB6002

Linear Low Density Polyethylene

Qenos Pty Ltd

Message:

ALKAMIX MB6002 is formulated with an antiblock additive at a concentration of 25 percent.

ALKAMIX MB6002 can be added to polyethylene during extrusion to reduce the blocking tendency of film. The level required may vary according to desired properties, however the recommended addition level is between 1 to 3 percent.

The maximum level of addition of MB6002 based on both good manufacturing practice and to ensure conformance to the requirements to the United States Food and Drug Administration Regulations CFR21 is 4 percent, when added to a polyethylene formulation free of any other additives.

| General Information | | | |
|---------------------|-----------------|-------------------|-------------|
| Additive | Antiblock (25%) | | |
| Features | Antiblocking | | |
| | High Clarity | | |
| Uses | Blending | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.980 | g/cm ³ | ASTM D1505 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT