

Trilene® HF7.0CP

Polypropylene Homopolymer
Chandra Asri Petrochemical

Message:

Trilene HF7.0CP is a polypropylene homopolymer for production of cast film.
This grade uses Unipol® polypropylene technology with the latest catalyst technology.

General Information			
Additive	Antiblock		
	Slip		
Features	Antiblocking		
	Good Processability		
	High Clarity		
	High Strength		
	Homopolymer		
	Slip		
Uses	Cast Film		
Agency Ratings	FDA 21 CFR 177.1520(c) 1.1		
Forms	Pellets		
Processing Method	Cast Film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.903	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	34.0	MPa	ASTM D638
Tensile Elongation (Yield)	13	%	ASTM D638
Flexural Modulus - 1% Secant ²	1280	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	35	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	104	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525 ³
Melting Temperature	163	°C	DSC, ASTM D3418
Extrusion	Nominal Value	Unit	
Melt Temperature	240 to 260	°C	

Take-Off Roll	25.0 to 30.0	°C
NOTE		
1.	50 mm/min	
2.	1.3 mm/min	
3.	Rate B (120°C/h)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

