

Ultrason® S 2010

Polysulfone

BASF Corporation

Message:

Ultrason S 2010 is an unreinforced, medium viscosity standard injection molding PSU grade. It flows readily and offers outstanding heat resistance and dimensional stability. Typical applications include automotive applications such as fuse encapsulation, connectors, heating system and headlight components and household applications requiring high heat resistance.

General Information			
UL YellowCard	E41871-233824		
Features	Good Dimensional Stability		
	Good Flow		
	High Heat Resistance		
	Medium Viscosity		
Uses	Automotive Electronics		
	Connectors		
	Electrical Parts		
	Household Goods		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Specific Volume vs Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (360°C/10.0 kg)	90.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.72	%	
Flow	0.68	%	
Water Absorption			ISO 62
Saturation, 23°C	0.80	%	

Equilibrium, 23°C, 50% RH	0.30	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	135	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2550	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	75.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	6.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	6.0	kJ/m ²	
23°C	5.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength			ISO 180
-30°C	6.0	kJ/m ²	
23°C	5.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	176	°C	ISO 75-2/A
CLTE - Flow	5.3E-5	cm/cm/°C	
RTI Elec			UL 746
1.60 mm	155	°C	
3.20 mm	155	°C	
RTI Imp			UL 746
1.60 mm	130	°C	
3.20 mm	130	°C	
RTI Str			UL 746
1.60 mm	155	°C	
3.20 mm	155	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms · cm	IEC 60093
Electric Strength	40	kV/mm	IEC 60243-1
Dielectric Constant			IEC 60250
100 Hz	3.10		
1 MHz	3.10		
Dissipation Factor			IEC 60250
100 Hz	8.0E-4		
1 MHz	6.4E-3		
Comparative Tracking Index	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Flame Rating		UL 94
1.60 mm	HB	
3.20 mm	V-2	
Injection	Nominal Value	Unit
Drying Temperature	130 to 150	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	340 to 390	°C
Mold Temperature	140 to 180	°C
Injection Pressure	3.50 to 12.5	MPa
Injection Rate	Fast	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

