

Sanren Q280 (Premium-grade)

Low Density Polyethylene

SINOPEC Shanghai Petrochemical Co. Ltd.

Message:

The oblate pellet product is colourless with excellent chemical stability. Under the normal conditions, the product is acid resistant, alkali resistant and salt resistant. It possesses certain mechanical properties and light transmittance.

Scope of Application: light-duty film, Laminated film and small size injection mouldings.

| General Information | |
|---------------------|--|
| Features | Low density Homopolymer alkali resistance acid resistance |
| Uses | Films Laminate |
| Appearance | Colorless |
| Forms | Particle |
| Processing Method | Blow molding Extrusion Injection molding |

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|--------------------------|-----------------|
| Density | 0.925 | g/cm ³ | Internal method |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 2.4 - 3.2 | g/10 min | Internal method |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | > 11.0 | MPa | Internal method |
| Tensile Elongation (Break) | > 550 | % | Internal method |
| Optical | Nominal Value | Unit | Test Method |
| Haze | < 10 | % | Internal method |
| Additional Information | Nominal Value | Unit | |
| Blocking | 0.0230 | MPa | |
| Fish Eye | | | |
| 0.300 to 2.00mm | | pcs/1200 cm ² | |
| Linking: 0.500 to 2.00mm | | pcs/20 cm ² | |
| Hue | | | |
| Impurities (> 100.0 μm) | | pcs/100 g | |
| Streaks | B | | |
| Cleanliness: <10 pieces/kg | | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

